

### SETSCO SERVICES PTE LTD

18 Teban Gardens Crescent Singapore 608925 Tel: (65) 6566 7777 Fax: (65) 6566 7718 Website: www.setsco.com Business Reg. No. 196900269D

### **TEST REPORT**

(This Report is issued subject to the terms & conditions set out below)

Your Ref:

Our Ref: MM-20692/LL/1

Date: 15 Oct 2010

(Supplementary Report No.: S/0075/11)

Page 1 of 2

Subject

Testing of Stainless Steel Wire Rope submitted by Invisys Technologies

Pte Ltd on 04 October 2010

**Tested For** 

INVISYS TECHNOLOGIES PTE LTD

26, Sin Ming Lane, #04-115

Midview City Singapore 573971

Attn: Mr. David Tan

**Date and Place** 

of Test

05 October 2010 at Setsco Laboratory

Method of Test:

**Tension Load Test** 

The test sample was clamped on the Universal Testing machine in a vertical position. Tension load was applied gradually until failure. The

maximum load was then recorded.

Description of

Sample

One (01) piece of stainless steel wire rope was received as follows:

S/ No	Description	Qty
1	Ø2.0 mm Stainless Steel Wire Rope	01

Results

Tension Load Test

Refer to Table attached.

LAWRENCE LIM **Testing Officer** 

CHENG KWANG MENG Manager (Mechanical Testing) Mechanical Technology Division

(3) The Report may not be used in any publicity material without the written consent of SETSCO. (4) The Report may not be reproduced in part or in full unless approval in writing has been given by SETSCO.

<sup>(1)</sup> The Report is prepared for the sole use of the Client and is prepared based upon the Item submitted, the services required by the Client and the conditions under which the Services are performed by SETSCO. The Report is not intended to be representative of similar or equivalent Services on similar or equivalent Items. The Report does not constitute an endorserment by SETSCO of the item.

(2) SETSCO agrees to use reasonable diligence in the performance of the Services but no warranties are given and none may be implied directly or indirectly relating to the Services, the Report or the facilities of SETSCO.

<sup>(5)</sup> SETSCO shall under no circumstances be liable to the Client or its agents, servants or representatives, in contract, tort (including negligence or breach of statutory duty) or otherwise for any direct or indirect loss or damage suffered by the Client, its agents, servants or representative howsoever arising or whether connected with the Services provided by SETSCO herein.



MM-20692/LL/1 (Supplementary Report No.: S/0075/11)

## Results:

# Table: Tension Load Test

Sample Reference	Ø2.0 mm Stainless Steel Wire Rope	
Measured Mean Diameter (mm)	2.0	
Maximum Load Applied (kN)	1.5 (152.9 kgf)	
Position of Failure	Fractured at the free length.	

Jan S

